

# 1) LUXLINE G + PUZZLELINE

## Indication of technical data

Product	Thickness fix (mm)	Substance approx. (g/m <sup>2</sup> )	Stiffness MD dynamic (mNm) ISO 5629	Stiffness CD dynamic (mNm) ISO 5629
1.a Unlined / Unlined	0,70 *	441	68	17
	0,80 *	504	93	30
	0,90 *	567	130	49
	1,00	630	170	75
	1,10	693	230	100
	1,20	756	275	135
	1,30	819	335	170
	1,40	882	375	225
1.c Grey / Grey	1,00 *	630	225	95
	1,10 *	693	285	130
	1,20 *	756	570	245
	1,25	787,5	575	250
	1,30	819	650	290
	1,40	882	800	350
	1,50	945	900	400
	1,60	1008	1.025	440
	1,70	1071	1.165	475
	1,75	1102,5	1.250	480
	1,80	1134	1.350	575
	1,90	1197	1.500	635
	2,00	1260	1.650	700
	2,10	1323	1.850	800
	2,20	1386	2.250	900
	2,30	1449	2.550	1.050
	2,40	1512	2.850	1.150
	2,50	1575	3.000	1.200
	2,70	1701	3.900	1.400
	2,80	1764	4.150	1.600
2,90	1827	4.250	1.700	
3,00	1890	4.750	1.850	
3,30	2079	Not standard product - on request		
3,60	2268	Not standard product - on request		
3,80	2394	Not standard product - on request		
1.e Grey / Grey XD	1,50	945	900	400
	1,75	1102,5	1.250	480
	1,90	1197	1.500	635
	2,00	1260	1.650	700
	2,20	1386	2.250	900
	2,40	1512	2.850	1.150
	2,50	1575	3.000	1.200
3,00	1890	4.750	1.850	
1.g PUZZLELINE Blue	1,50	945	900	400
	1,75	1102,5	1.250	480
	1,80	1134	1.350	575
	1,90	1197	1.500	645
1.i PUZZLELINE Blue Unlined	1,30	819	in development	in development
Moisture (%)			8,25 (XD = 7,00)	
Tolerance Moisture (%)			+/- 1	
Tolerance Thickness (%)			+/- 3	
Plybond DIN 54516 (N/min)			40	
FSC Certificate			FSC® recycled 100% CU-COC-810587	
Machine width (cm)			215-230 * / 263-274	