

PRODUCT INFORMATION

MONOTEX L 125 BG



| PROPERTY | UNITY | | TOLERANCE | STANDARD |
|-------------------|------------------|---------------------------|-----------|--------------|
| Weight | g/m ² | 186 | ± 10 % | ISO 4591 |
| Thickness | µm | 135 | ± 10 % | ISO 4593 |
| Smoothness (Bekk) | 1.Side 2.Side | s 20 20 | min. | ISO 5627 |
| Heat resistance | °C | - 40 to + 180, 30 Min. | | |
| Opacity | % | 93 | min | ISO 2471 |
| Tensile strength | along cross | MPa 80 100 | min. | ISO 527-1 |
| Weight of coating | g/m ² | 5 each Side | ± 1 | Féron intern |

This product features a good water resistance without mechanical load.

Printability:

Flexo, Offset, Silk screen printing, thermaltransfer printing, laser printing.

The product must be stored at standard climate conditions (23 °C / 50 % relative humidity).

Unless otherwise agreed upon, the suitability of our products supplied for the specific production process or application is not a term of the sales contract. The customer alone is responsible for testing our products with regard to his particular application.

The above information corresponds to our current state of knowledge. Our products are subject to modification when mandatory caused by e.g. adjustment of legal requirements or raw material modifications of our suppliers.

All values stated above are to be considered as average values. This is not a specification. We reserve the right to make technical changes.